



EASTERN POLY CO., LTD

WOVEN GEO-TEXTILES 170 GRAM PER SQUARE METER

Minimum Average Roll Values when tested in accordance with the ASTM methods listed below.

Property	Test Method	Imperial	Metric
Wide Width Tensile	ASTM D-4595	n/a	32 Kn/m
Grab Tensile Strength	ASTM D-4632	200 lbs	890 N
Elongation	ASTM D-4632	16 %	16 %
Puncture	ASTM D-4833	90 lbs	400 N
Mullen Burst	ASTM D-3786	460 psi	3170 kpa
Trapezoidal Tear	ASTM D-4533	200 lbs	890 N
UV Resistance (retained after 1200 hrs)	ASTM D-4355	70 %	70 %
Apparent Opening Size	ASTM D-4751	40 US Sieve	0.425 mm
Permittivity	ASTM D-4491	0.05 sec-1	0.05 sec-1
Flow Rate	ASTM D-4491	4 gpm/ft ²	163 lpm/m ²

Seller makes no warranty, expressed or implied, concerning the product furnished hereunder other than at the time of delivery it shall be of the quality and specification stated herein.