



EASTERN POLY CO., LTD

WOVEN GEO-TEXTILES 270 GRAM PER SQUARE METER

Minimum Average Roll Values when tested in accordance with the ASTM methods listed below.

Property	Test Method	Imperial	Metric
Wide Width Tensile	ASTM D-4595	n/a	44 Kn/m
Grab Tensile Strength	ASTM D-4632	400 lbs	2089 N
Elongation	ASTM D-4632	18 %	18 %
Puncture	ASTM D-4833	185 lbs	815 N
Mullen Burst	ASTM D-3786	800 psi	5500 kpa
Trapezoidal Tear	ASTM D-4533	185 lbs	815 N
UV Resistance (retained after 1200 hrs)	ASTM D-4355	70 %	70 %
Apparent Opening Size	ASTM D-4751	30 US Sieve	0.60 mm
Permittivity	ASTM D-4491	0.35 sec-1	0.35 sec-1
Flow Rate	ASTM D-4491	30 gpm/ft ²	1200 lpm/m ²

Seller makes no warranty, expressed or implied, concerning the product furnished hereunder other than at the time of delivery it shall be of the quality and specification stated herein.